

**AMENDMENTS TO THE SPECIFICATION:**

Please replace the last paragraph on page 6 with the following amended paragraph:

B<sup>1</sup>

An organic light-emitting device according to a fifth embodiment of the present invention is shown in Figure 5. This device is similar to that shown in Figure 4 except that a sputtered layer of aluminium 20 having a thickness of about 10 microns is provided between the evaporated aluminium layer 14 and the second layer of calcium 18 as an additional barrier layer. According to a further variation as shown in Figure 6, a further sputtered layer of aluminium 22 is provided between the second calcium layer 18 and the aluminium nitride layer 12.

FINNEGAN  
HENDERSON  
FARABOW  
GARRETT &  
DUNNER LLP

1300 I Street, NW  
Washington, DC 20005  
202.408.4000  
Fax 202.408.4400  
[www.finnegan.com](http://www.finnegan.com)